

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
20 January 2005 (20.01.2005)

PCT

(10) International Publication Number  
**WO 2005/005492 A1**

(51) International Patent Classification<sup>7</sup>: **C08F 10/00**

(21) International Application Number:  
PCT/EP2004/051261

(22) International Filing Date: 28 June 2004 (28.06.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
03102021.7 4 July 2003 (04.07.2003) EP

(71) Applicant (for all designated States except US): ATO-  
FINA RESEARCH [BE/BE]; Zone Industrielle C, B-7181  
Seneffe (Feluy) (BE).

(72) Inventor; and

(75) Inventor/Applicant (for US only): RAZAVI, Abbas  
[IR/BE]; 35, Domaine de la Brisée, B-7000 Mons (BE).

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,  
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,  
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,  
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,  
ZW.

(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,  
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,  
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,  
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,  
GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.

(54) Title: RANDOM OLEFIN COPOLYMERS

(57) Abstract: Provided is a method for the production of an olefin co-polymer, which method comprises co-polymerising two or more olefin monomers in the presence of a metallocene catalyst, wherein the metallocene catalyst comprises a metallocene hav-  
ing the following formula:  $R''(CpR_m)(FluR'_n)MQ_2$  wherein Cp comprises a cyclopentadienyl ring; Flu comprises a fluorenyl ring;  
R''comprises a structural bridge imparting stereorigidity to the component; each R is the same or different and is an organic group;  
m is an integer of from 1-4; each R' is the same or different and is an organic group; n is an integer of from 0-8; M is a metal atom  
from group IVB of the Periodic Table or is vanadium; and each Q is a hydrocarbon having from 1-20 carbon atoms or is a halogen.